

Nano-Seal ST60

Revised: 11.09.2017

General description:

Nano-Seal ST60 is a very low viscous two component impregnant. Nano-Seal ST60 penetrates into micropores by capillary forces. Contains solvents.

Specific properties:

- Very good chemical resistance (due to the dense polymer network after curing).
- Very good thermal resistance.
- Very good corrosion resistance.
- Good leveling and wetting.
- Very good adhesion on a variety of materials.
- High strength.
- Contains solvents.

Application areas:

Nano-Seal ST60 is used as impregnant for thermally sprayed coatings. In particular if chemical resistance is mandatory.

Technical data at 20°C¹⁾:

Color:	Colorless to pale yellow, slightly opaque
Spec. weight:	1,1 g/cm ³
Shore-D:	> 80
Thermal resistance dry:	130°C
Thermal resistance wet:	80°C
Viscosity:	Brookfield: ca. 5 - 10 mPas at 25°C

Chemical Resistance (20°C)¹⁾:

Mineral oil	1	Ketones (generally)	2
Petrol	1	Acetone	2-3
Hydrochloric acid up to 10 %	1	Esters (generally)	1-2
Hydrochloric acid up to 20 %	1-2	Ethyl acetate	2
Sulphuric acid up to 10 %	1-2	Chlorinated hydrocarbons (gen.)	2-3
Caustic soda up to 30 %	1	Methylene chloride	3
Conc. Potassium hydroxyde	1	Toluene	1-2
Conc. Ammonium hydroxyde	1	Refrigerants	1-2
Acetic acid up to 5 %	2	Naphta	1
Salt water	1	Diesel	1

1: Fully resistant

2: Short immersion possible

3: Resistant when immediately wiped off

4: Not resistant

1) Please note: There is a decrease of the chemical resistance, hardness, strength and adhesion at elevated temperature.

Delivery form:

Transparent pale yellow liquid

Quantities of a set with resin and hardener: 200 g, 0,8 L and 6 L

Nano-Seal ST60

Revised: 11.09.2017

Processing

- Remove all soiling (ideal is acetone). In particular oils and grease have to be removed thoroughly. Afterwards dry the surface.
- Roughen the surface up to about 100 µ. Sand blasting is ideal (when used as a coating and adhesion is crucial).
- Mix resin (component A) and hardener (component B) in the correct mixing ratio as indicated below. Make sure that all zones of the container are stirred.
- Mix only quantities which can be processed within the pot life. Do not mix more than 500 g in one go.

Processing Modes:

Nano-Seal ST60 is applied by rolling, brushing and spraying.

Conditions for Processing:

Minimum temperature: 10°C
Max. humidity: 80 %
Temperature of the surface to be coated: At least 3°C above dew point

Mixing Ratio (by weight):

Resin:	4,0			
Hardener:	1			
Typical quantities:	100 g	250 g	500 g	
Resin:	80	200	400	
Hardener:	20	50	100	

Pot Life (20°C, 100 g):

Ca. 20 min.

Curing (thin layer) at 25°C:

Light mechanical load: after 8 h
Full mechanical load: after 24 h
Chemically fully resistant: after 96 h (annealing at 90°C/2h increases the chemical resistance significantly)
Curing speed depends highly on the thickness of the layer.

Coverage:

Coverage of one sqm (thickness: 0,1 mm) requires 0,11 kg.

Additional Information:

Storage: Below 35°C; close container thoroughly.
Shelf life: The material can be stocked in originally closed containers for at least 12 month.

Safety:

Read material safety data sheet prior to use.
Nano-Seal ST60 gets very hot upon curing. Do not mix more than 500 g.

The technical data mentioned in this technical data sheet have to be regarded as rough guidelines. They have been obtained in our laboratory under optimal conditions. For the suitability of the product for specific applications we do not take the responsibility and we deny any liability. We recommend to do trials under conditions which reflect the individual practical application prior to the use of the material for the real application.